

## MAK ELASTOTHANE EMB

POLYURETHANE BASED ELASTOMERIC  
WATERPROOFING MEMBRANE



### Product Description

Mak Elastothane EMB is a liquid applied polyurethane based heavy-duty elastomeric membrane coating. Mak Elastothane EMB when applied on a surface, gives a continuous monolithic film which is rubbery and elastic in nature. The film is self-curing and cures by reaction with atmospheric moisture to give a tough elastomeric waterproof membrane.

Mak Elastothane EMB has good adhesion to a wide range of substrates such as concrete, brick, wood, slates, tiles, glass and metals etc. This is supplied also as a medium grade for roller, squeegee or brush application to horizontal as well as vertical surface.

### Primary Applications

The high elasticity, excellent bond strength with concrete and other substrates, low water permeability of Mak Elastothane EMB makes it ideal membrane coating for a wide range of water / vapour proofing applications such as:

- ◆ Foundations, Basements, Lift pits.
- ◆ Car decks, Podiums.
- ◆ Roof, terraces, Balconies, Patios.
- ◆ Sewage works and Sunken Portions.

The excellent chemical resistance of Mak Elastothane EMB is used as a barrier coating for any part of the external or internal faces of the structures where high degree of waterproofing is required.

### Directions for Use

1. Clean the surface thoroughly with wire brush, remove all dust, dirt, foreign Particles, fungi, etc.
2. Allow surface to be completely dry. Do not apply Mak Elastothane EMB on damp surface.
3. All the cracks/voids shall be sealed with rubberized Mak Sealing Compound (ISI)
4. Apply Mak PU Primer at 3-4 Sqm/Ltr on the entire surface to be treated. Alternatively, dilute Mak Elastothane EMB in the ratio of 1:1 with water. Allow the primer to dry.

5. Apply Mak Elastothane EMB by brush or spray at 0.8-0.9 kg/sqm on the entire surface and up to 300 mm high on parapet wall. Allow it to dry.
6. Apply second coat of Mak Elastothane EMB at 0.8-0.9 kg/sqm to achieve total dry film thickness of 1.5mm.
7. Reinforcement of Non-woven Polyester or Glass fiber of 40-45gsm may be provided between the layers for improved tensile strength.

### Coverage

Mak PU Primer: 3-4 Sqm/l.

Mak Elastothane EMB: 1.6-1.8 kg/Sqm on a smooth surface will provide an adequate film thickness of approx. 1.5 mm.

\*Coverage rates may vary with surface texture and porosity.

### Storage

Store in cool and dry place. Lid of the container should be properly closed after use. In very cold conditions store inside. Do not attempt to thin. Once opened Mak Elastothane EMB will start to cure and a skin will form, even in the resealed cans. This can be removed if material is used within approximately one month.

## Technical Specifications

Specific Gravity	:	1.18
Abel Closed Cup Flash Point	:	56°C
Approximate drying time	:	6-8 hours per coat
Elongation	:	>800%
Solid contents	:	>80%
Hardness, Shore A (After 7 days)	:	>50
Shelf life	:	12 months
Service Temperature	:	-20°C to 60°C or even more, only air curing takes more time at low temp.

## Health and Safety:

- ◆ Keep away from sources of ignition
- ◆ Do not breathe vapour/spray
- ◆ Ensure good ventilation during application and drying
- ◆ In case of eye contact-wash with plenty of clean water and seek medical advice.
- ◆ Avoid prolonged skin contact wear suitable protective clothing and gloves while handling/applying.
- ◆ Remove from skin with mild solvent/hand cleanser and wash with warm soapy water.

### M.K. PETRO PRODUCTS INDIA PVT. LTD

[ AN ISO 9001 Certified Company ]

Village Mujeri Road, Ballabhgarh, Faridabad

Ph: +91-9560096816

Toll-free: 1800-103-9664

Website: [www.makphalt.com](http://www.makphalt.com)

Email: [info@makphalt.com](mailto:info@makphalt.com)

